KARNATAKA STATE ROAD TRANSPORT CORPORATION
CENTRAL OFFICES,
MECHANICAL ENGG (M) DEPT.

Specification/Properties for Synthetic Rubber Adhesive 998

Solvent	Toluene
Colour/Appearance	Brown/Dark Brown
Viscosity@30° ± 1°C	20-25 Poise(1Poise=1gram/Cm-Sec)@30°C
Specific Gravity	0.85-0.90
Temperature Resistance	30 °C to 96°C
Solvent Drying time	15-20 minutes
Tack development time	10-15 minutes
Tack Retention time	15-30 minutes
Coverage by speeder	4.0m^2-5. 0m^2/Litre/Coat
Flash Point	-40°C
Packing	5 Ltrs. Tin
Fields of application	1)Bus roof top/flooring and upholstery 2)Plywood/Metal to Foam/Rexene/Leather
Shelf Life	1 year from the date of manufacture under recommended storage conditions and in a sealed container
Storage	Highly Inflammable material

Chief Mechanical Engineer (M)